



## Acco Stone Quarry

1st Quarter 2025

Specific Gravity: 2.791

L.A. Abrasion (%): 22.3

Soundness: 0.4

### Average Gradation Percent Passing

#### Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#30	#50	#100	#200
57			100.00%	100.00%	79.49%	28.43%	9.15%	2.30%	1.30%					
68				100.0%	95.3%	64.1%	36.7%	4.6%	1.6%	1.3%				
78					100.0%	96.3%	67.5%	8.8%	2.2%	1.7%				
8						100.0%	88.0%	9.7%	2.3%					
10							100.0%	95.3%	57.8%	35.4%	24.0%	18.2%	14.4%	11.7%
Man. Sand							100.0%	100.0%	97.7%	60.4%	28.3%	14.4%	6.3%	2.0%

#### Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				97.40%	69.19%	49.80%	29.72%	22.24%				