



Galax Quarry

1st Quarter 2024

Specific Gravity: 2.786

L.A. Abrasion (%): 21.8

Soundness: 13.7

Average Gradation Percent Passing

Course Aggregate

| Sieve Size | 2 1/2" | 2" | 1 1/2" | 1" | 3/4" | 1/2" | 3/8" | #4 | #8 | #16 | #50 | #100 | #200 |
|------------|--------|----|---------|---------|--------|--------|-------|-------|-------|-----|-----|------|------|
| 57 | | | 100.00% | 100.00% | 97.79% | 43.70% | 9.90% | 4.40% | 3.90% | | | | |

Dense Graded Aggregate

| Sieve Size | 2 1/2" | 2" | 1 1/2" | 1" | 3/4" | 1/2" | 3/8" | #4 | #10 | #16 | #40 | #200 |
|------------|--------|----|--------|--------|--------|--------|--------|--------|-----|-----|-----|------|
| 26 | | | | 84.35% | 69.60% | 60.30% | 50.00% | 40.00% | | | | |