



Dublin Quarry

1st Quarter 2025

Specific Gravity: 2.69

L.A. Abrasion (%): 15.62

Soundness: 7.07

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100
57			100.00%	99.16%	76.71%	29.42%	6.31%	1.92%	1.48%			
68				100.00%	94.46%	94.46%	56.52%	19.54%	6.30%	3.69%		
8						100.00%	91.65%	7.04%	1.76%			
10							100.0%	96.6%	57.4%	26.7%	14.2%	10.6%

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	93.98%	68.95%	55.90%	31.96%				