



## Dublin Quarry

4th Quarter 2022

Specific Gravity: 2.69

L.A. Abrasion (%): 15.62

Soundness: 7.07

### Average Gradation Percent Passing

#### Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100
57			100.00%	100.00%	83.18%	44.25%	18.88%	3.04%	2.48%			
68				100.00%	94.46%	94.46%	56.52%	19.54%	6.30%	3.69%		
8						100.00%	96.79%	24.93%	2.64%			
10							100.0%	97.5%	58.0%	31.1%	9.8%	7.6%

#### Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	96.40%	79.83%	68.42%	33.35%				