

Rocky Gap Quarry

1st Quarter 2025

Specific Gravity:	2.75	L.A. Abrasion (%):	18.3	Soundness:	6.87
-------------------	------	--------------------	------	------------	------

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100	#200
57			100.00%	100.00%	86.58%	28.83%	7.29%	1.73%	1.57%				

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	96.78%	70.06%	45.62%	27.03%				