



Shawsville Quarry

Quarter

Specific Gravity: 2.8

L.A. Abrasion (%): 18.4

Soundness: 0.5

Average Gradation Percent Passing

Course Aggregate

Sieve Size	4"	3 1/2"	3"	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16
57						100.00%	100.00%	100.00%	33.23%	33.23%	1.59%	1.43%	
68							100.00%	99.36%	99.36%	58.69%	6.71%	2.51%	2.13%
78								100.0%	90.6%	61.8%	7.5%	2.6%	1.6%
8									99.7%	88.1%	12.8%	1.3%	0.9%

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	92.99%	92.99%	92.99%	29.23%				