



Sylvatus Quarry

1st Quarter 2025

Specific Gravity: 2.7

L.A. Abrasion (%): 19.5

Soundness: 18.7

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100
57				100.00%	94.73%	42.71%	12.89%	2.15%	1.93%			
78					100.0%	91.9%	67.6%	15.0%	3.6%	2.6%		
SMA7					100.0%	84.1%	51.7%	3.6%				
8						100.0%	89.0%	23.1%	6.0%	3.6%		

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	97.69%	78.32%	66.39%	41.60%				