



Wythe Stone and Sand

1st Quarter 2024

Specific Gravity: 2.798

L.A. Abrasion (%): 17.2

Soundness: 3.8

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#30	#50	#100	#200
57			100.00%	100.00%	93.49%	31.65%	5.44%	2.68%	2.35%					
68				100.0%	96.5%	56.8%	27.8%	6.4%	3.6%					
10							100.0%	88.3%	44.7%	22.5%	13.5%	9.0%	6.6%	

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	93.77%	76.61%	65.09%	36.73%				

Sand

Sieve Size	FM	3/8"	#4	#8	#16	#30	#50	#100	#200
Concrete	2.62	100.00%	95.78%	87.72%	78.46%	54.78%	17.30%	3.84%	1.27%
Mortar	2.46	100.00%	100.00%	99.20%	86.22%	41.37%	18.20%	8.93%	

Specific Gravity: 2.639

L.A. Abrasion (%): 0.3

Soundness: 13.9