



Wythe Stone and Sand

1st Quarter 2025

Specific Gravity: 2.798

L.A. Abrasion (%): 17.2

Soundness: 3.8

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#30	#50	#100	#200
57			100.00%	100.00%	91.40%	42.03%	17.17%	4.18%	3.39%					
68				100.0%	96.2%	59.2%	32.6%	7.2%	4.2%					
10							86.1%	36.7%	17.8%	11.3%	8.1%	6.1%	4.4%	

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				99.83%	92.75%	74.86%	52.34%	33.69%				

Sand

Sieve Size	FM	3/8"	#4	#8	#16	#30	#50	#100	#200
Concrete	2.57	100.00%	96.32%	88.51%	78.64%	57.00%	18.27%	3.83%	1.15%
Mortar	1.81	100.00%	99.88%	99.49%	97.15%	79.06%	33.44%	10.43%	3.68%

Specific Gravity: 2.639

L.A. Abrasion (%): 0.3

Soundness: 13.9